

FOXAZINC-EP (OX-301)

Zinc Epoxy Primer

PRODUCT DESCRIPTION	Polyamide cured zinc epoxy primer																																		
RECOMMENDED USE	A zinc primer for applications in aggressive environments in a wide range of industries and to repair organic / inorganic zinc primer.																																		
CHARACTERISTICS	<ul style="list-style-type: none"> • Excellent adhesion to inorganic zinc primer. • Good corrosion prevention properties • Quick drying and can be over coated after a short interval. • Excellent abrasion resistance which minimize transit and handling damages. • Not recommended for immersion service in acid and alcohols. 																																		
PHYSICAL DATA	<table border="0"> <tr> <td>Colour</td> <td>Grey</td> </tr> <tr> <td>Gloss Level</td> <td>Flat</td> </tr> <tr> <td>Volume Solid</td> <td>Approx. 50%</td> </tr> <tr> <td>Dry Film Thickness</td> <td>75 microns per coat</td> </tr> <tr> <td>Number of Coat</td> <td>1</td> </tr> <tr> <td>Theoretical Coverage</td> <td>6.60 sq.m/ℓ for 75 microns</td> </tr> <tr> <td>Temperature Resistance</td> <td>Maximum : 93⁰C (dry)</td> </tr> <tr> <td>VOC</td> <td>449 g/ℓ</td> </tr> <tr> <td>Flash Point</td> <td>Base : 37⁰C Hardener : 37⁰C</td> </tr> <tr> <td>Shelf Life</td> <td>At least 12 months</td> </tr> <tr> <td>Pack Size</td> <td>20 Kgs units</td> </tr> <tr> <td></td> <td>Base : 16 Kgs , Hardener : 4 Kgs</td> </tr> </table>	Colour	Grey	Gloss Level	Flat	Volume Solid	Approx. 50%	Dry Film Thickness	75 microns per coat	Number of Coat	1	Theoretical Coverage	6.60 sq.m/ℓ for 75 microns	Temperature Resistance	Maximum : 93 ⁰ C (dry)	VOC	449 g/ℓ	Flash Point	Base : 37 ⁰ C Hardener : 37 ⁰ C	Shelf Life	At least 12 months	Pack Size	20 Kgs units		Base : 16 Kgs , Hardener : 4 Kgs										
Colour	Grey																																		
Gloss Level	Flat																																		
Volume Solid	Approx. 50%																																		
Dry Film Thickness	75 microns per coat																																		
Number of Coat	1																																		
Theoretical Coverage	6.60 sq.m/ℓ for 75 microns																																		
Temperature Resistance	Maximum : 93 ⁰ C (dry)																																		
VOC	449 g/ℓ																																		
Flash Point	Base : 37 ⁰ C Hardener : 37 ⁰ C																																		
Shelf Life	At least 12 months																																		
Pack Size	20 Kgs units																																		
	Base : 16 Kgs , Hardener : 4 Kgs																																		
SURFACE PREPARATION	Dry abrasive blast in accordance with ISO – Sa 2.5 or SSPC – SP 10 “Near White”. Blast to achieve a 25 – 50 microns anchor profile as indicate with a Keane Tator Surface Profile Comparator. Remove abrasive residue or dust from surface.																																		
APPLICATION DATA	<table border="0"> <tr> <td colspan="2">Application Methods</td> </tr> <tr> <td>Airless Spray</td> <td></td> </tr> <tr> <td> Nozzle Tip</td> <td>Approx. 0.46 mm (0.018 inch)</td> </tr> <tr> <td> Nozzle Pressure</td> <td>10 MPa (approx. 1400 psi)</td> </tr> <tr> <td>Conventional Spray</td> <td></td> </tr> <tr> <td> Nozzle Tip</td> <td>Approx. 1.8 mm (0.071 inch)</td> </tr> <tr> <td> Nozzle Pressure</td> <td>0.3 MPa (approx. 43 psi)</td> </tr> <tr> <td>Brush or Roller</td> <td>Only for touch up</td> </tr> <tr> <td>Mixing Ratio By Volume</td> <td>Base : Hardener = 4 : 1</td> </tr> <tr> <td>Thinner</td> <td>FOXANER 003</td> </tr> <tr> <td>Surface Temperature</td> <td>Should be 10⁰C – 50⁰C, at least 3⁰C above the dew point to prevent condensation</td> </tr> <tr> <td colspan="2">Drying Time</td> </tr> <tr> <td> Touch Dry</td> <td>25 minutes at 25⁰C, 15 minutes at 32⁰C</td> </tr> <tr> <td> Through Dry</td> <td>40 minutes at 25⁰C, 25 minutes at 32⁰C</td> </tr> <tr> <td> To Topcoat</td> <td>8 hours at 25⁰C, 4 hours at 32⁰C</td> </tr> <tr> <td>Pot Life</td> <td>24 hours at 25⁰C, 12 hours at 32⁰C</td> </tr> <tr> <td>Limitation</td> <td>Zinc rich primers can form zinc salts on the surfaces, before over coating visible surface contamination must be removed by high pressure water cleaning, sweep blasting or mechanical cleaning.</td> </tr> </table>	Application Methods		Airless Spray		Nozzle Tip	Approx. 0.46 mm (0.018 inch)	Nozzle Pressure	10 MPa (approx. 1400 psi)	Conventional Spray		Nozzle Tip	Approx. 1.8 mm (0.071 inch)	Nozzle Pressure	0.3 MPa (approx. 43 psi)	Brush or Roller	Only for touch up	Mixing Ratio By Volume	Base : Hardener = 4 : 1	Thinner	FOXANER 003	Surface Temperature	Should be 10 ⁰ C – 50 ⁰ C, at least 3 ⁰ C above the dew point to prevent condensation	Drying Time		Touch Dry	25 minutes at 25 ⁰ C, 15 minutes at 32 ⁰ C	Through Dry	40 minutes at 25 ⁰ C, 25 minutes at 32 ⁰ C	To Topcoat	8 hours at 25 ⁰ C, 4 hours at 32 ⁰ C	Pot Life	24 hours at 25 ⁰ C, 12 hours at 32 ⁰ C	Limitation	Zinc rich primers can form zinc salts on the surfaces, before over coating visible surface contamination must be removed by high pressure water cleaning, sweep blasting or mechanical cleaning.
Application Methods																																			
Airless Spray																																			
Nozzle Tip	Approx. 0.46 mm (0.018 inch)																																		
Nozzle Pressure	10 MPa (approx. 1400 psi)																																		
Conventional Spray																																			
Nozzle Tip	Approx. 1.8 mm (0.071 inch)																																		
Nozzle Pressure	0.3 MPa (approx. 43 psi)																																		
Brush or Roller	Only for touch up																																		
Mixing Ratio By Volume	Base : Hardener = 4 : 1																																		
Thinner	FOXANER 003																																		
Surface Temperature	Should be 10 ⁰ C – 50 ⁰ C, at least 3 ⁰ C above the dew point to prevent condensation																																		
Drying Time																																			
Touch Dry	25 minutes at 25 ⁰ C, 15 minutes at 32 ⁰ C																																		
Through Dry	40 minutes at 25 ⁰ C, 25 minutes at 32 ⁰ C																																		
To Topcoat	8 hours at 25 ⁰ C, 4 hours at 32 ⁰ C																																		
Pot Life	24 hours at 25 ⁰ C, 12 hours at 32 ⁰ C																																		
Limitation	Zinc rich primers can form zinc salts on the surfaces, before over coating visible surface contamination must be removed by high pressure water cleaning, sweep blasting or mechanical cleaning.																																		

SYSTEM COMPATIBILITY

Before over coating with recommended topcoat ensure the OX-301; FOXAZINC PRIMER is fully cured and if weathering has occurred all zinc salt should be removed from the surface by fresh water washing, and if necessary scrubbing with bristle brushes.

In some cases it may be necessary to apply a mist coat of suitable viscosity to minimise bubbling. This will depend upon the age of the OX-301; FOXAZINC PRIMER, surface roughness and ambient conditions during curing and application.

For other suitable intermediates or topcoat, please consult FOXAPAIN Industrial Coatings.

SAFETY PRECAUTION

Keep away from heat, spark and Open flames. Avoid breathing of vapour on skin and eye contact. Keep container closed and store in cool, ventilated area when not in use.

Proper ventilation and protective measures must be provided during mixing, application and drying, to keep vapour concentration within safe limits and to protect against toxic hazard.

Necessary safety equipment must be used and ventilation requirements carefully observed, especially in confined or enclosed spaces, such as tank interior and building.

DISCLAIMER

The information in this product data sheet is given to the best of our knowledge based on laboratory testing and practical experience. If the product is used under condition beyond our control, we cannot guarantee anything but the quality of the products it self. The information in this product data sheet is liable for modification from time to time in the light of experience and our policy of continuous product development, and without further notice.

ISSUED: **January 2009**