

Product Data Sheet

FOXA ETCH (OX-502)

Epoxy Etch Primer

PRODUCT DESCRIPTION	A single pack epoxy vinyl etch primer.																										
RECOMMENDED USE	Specifically designed as a primer for stainless steel, aluminium, galvanized irons, brass, copper, and chrome; to provide good adhesion for subsequent coats.																										
CHARACTERISTICS	<ul style="list-style-type: none"> • Excellent anti corrosive. • May be over coated with most finishing type. • Excellent adhesion to most metals. • May be left uncoated for up to three months before it needs to be over coated. 																										
PHYSICAL DATA	<table border="0"> <tr> <td>Colour</td> <td>Off White, Green, Black, Grey</td> </tr> <tr> <td>Gloss Level</td> <td>Semi Gloss</td> </tr> <tr> <td>Volume Solid</td> <td>Approx. 10%</td> </tr> <tr> <td>Dry Film Thickness</td> <td>10 – 20 microns per coat</td> </tr> <tr> <td>Number of Coat</td> <td>1</td> </tr> <tr> <td>Theoretical Coverage</td> <td>10.00 sq.m/ℓ for 10 microns</td> </tr> <tr> <td>Temperature Resistance</td> <td>Maximum : 115⁰C (dry)</td> </tr> <tr> <td>VOC</td> <td>711 g/ℓ</td> </tr> <tr> <td>Flash Point</td> <td>16⁰C</td> </tr> <tr> <td>Shelf Life</td> <td>At least 12 months</td> </tr> <tr> <td>Pack Size</td> <td>20 Kgs</td> </tr> </table>	Colour	Off White, Green, Black, Grey	Gloss Level	Semi Gloss	Volume Solid	Approx. 10%	Dry Film Thickness	10 – 20 microns per coat	Number of Coat	1	Theoretical Coverage	10.00 sq.m/ℓ for 10 microns	Temperature Resistance	Maximum : 115 ⁰ C (dry)	VOC	711 g/ℓ	Flash Point	16 ⁰ C	Shelf Life	At least 12 months	Pack Size	20 Kgs				
Colour	Off White, Green, Black, Grey																										
Gloss Level	Semi Gloss																										
Volume Solid	Approx. 10%																										
Dry Film Thickness	10 – 20 microns per coat																										
Number of Coat	1																										
Theoretical Coverage	10.00 sq.m/ℓ for 10 microns																										
Temperature Resistance	Maximum : 115 ⁰ C (dry)																										
VOC	711 g/ℓ																										
Flash Point	16 ⁰ C																										
Shelf Life	At least 12 months																										
Pack Size	20 Kgs																										
SURFACE PREPARATION	All loose material should be removed by wire brush or mechanical sander. Remove all dirt, oil and grease. Light abrasive blast is recommended.																										
APPLICATION DATA	<table border="0"> <tr> <td colspan="2">Application Methods</td> </tr> <tr> <td>Conventional Spray</td> <td></td> </tr> <tr> <td> Nozzle Tip</td> <td>1.8 mm (0.071 inch)</td> </tr> <tr> <td> Nozzle Pressure</td> <td>0.3 MPa (approx. 43 psi)</td> </tr> <tr> <td>Brush</td> <td>For small area</td> </tr> <tr> <td>Mixing Ratio</td> <td>One Component</td> </tr> <tr> <td>Thinner</td> <td>FOXANER 005</td> </tr> <tr> <td>Surface Temperature</td> <td>Should be 10⁰C – 49⁰C, at least 3⁰C above the dew point to prevent condensation</td> </tr> <tr> <td colspan="2">Drying Time</td> </tr> <tr> <td>Touch Dry</td> <td>5 minutes at 25⁰C, 3 minutes at 32⁰C</td> </tr> <tr> <td>Hard Dry</td> <td>20 minutes at 25⁰C, 10 minutes at 32⁰C</td> </tr> <tr> <td>To Topcoat</td> <td>2 hours at 25⁰C, 1 hour at 32⁰C</td> </tr> <tr> <td></td> <td>May be over coated up to three months after application, ensure surface is clean, dry and free from any contaminations.</td> </tr> </table>	Application Methods		Conventional Spray		Nozzle Tip	1.8 mm (0.071 inch)	Nozzle Pressure	0.3 MPa (approx. 43 psi)	Brush	For small area	Mixing Ratio	One Component	Thinner	FOXANER 005	Surface Temperature	Should be 10 ⁰ C – 49 ⁰ C, at least 3 ⁰ C above the dew point to prevent condensation	Drying Time		Touch Dry	5 minutes at 25 ⁰ C, 3 minutes at 32 ⁰ C	Hard Dry	20 minutes at 25 ⁰ C, 10 minutes at 32 ⁰ C	To Topcoat	2 hours at 25 ⁰ C, 1 hour at 32 ⁰ C		May be over coated up to three months after application, ensure surface is clean, dry and free from any contaminations.
Application Methods																											
Conventional Spray																											
Nozzle Tip	1.8 mm (0.071 inch)																										
Nozzle Pressure	0.3 MPa (approx. 43 psi)																										
Brush	For small area																										
Mixing Ratio	One Component																										
Thinner	FOXANER 005																										
Surface Temperature	Should be 10 ⁰ C – 49 ⁰ C, at least 3 ⁰ C above the dew point to prevent condensation																										
Drying Time																											
Touch Dry	5 minutes at 25 ⁰ C, 3 minutes at 32 ⁰ C																										
Hard Dry	20 minutes at 25 ⁰ C, 10 minutes at 32 ⁰ C																										
To Topcoat	2 hours at 25 ⁰ C, 1 hour at 32 ⁰ C																										
	May be over coated up to three months after application, ensure surface is clean, dry and free from any contaminations.																										
SAFETY PRECAUTION	<p><i>Keep away from heat, spark and Open flames. Avoid breathing of vapour on skin and eye contact. Keep container closed and store in cool, ventilated area when not in use. Proper ventilation and protective measures must be provided during mixing, application and drying, to keep vapour concentration within safe limits and to protect against topic hazard.</i></p> <p><i>Necessary safety equipment must be used and ventilation requirements carefully observed, especially in confined or enclosed spaces, such as tank interior and building.</i></p>																										
DISCLAIMER	<p><i>The information in this product data sheet is given to the best of our knowledge based on laboratory testing and practical experience. If the product is used under condition beyond our control, we cannot guarantee anything but the quality of the products it self. The information in this product data sheet is liable for modification from time to time in the light of experience and our policy of continuous product development, and without further notice.</i></p>																										