

## FOXAPOX ZONE (OX-503)

### Modified Epoxy

<b>PRODUCT DESCRIPTION</b>	High solids modified cured epoxy coating.																																				
<b>RECOMMENDED USE</b>	Designed for offshore splashzone maintenance where its continued cure under immersed conditions is required. May be applied to slightly damp surfaces.																																				
<b>CHARACTERISTICS</b>	<ul style="list-style-type: none"> <li>• Excellent durability in marine atmosphere</li> <li>• Resist splash, spillage and fumes of mild acids, alkalises, salts solutions and solvents.</li> <li>• Build coat or finish coat for the protection of steel and concrete in structure exposed to aggressive atmospheric condition.</li> </ul>																																				
<b>PHYSICAL DATA</b>	<table border="0"> <tr> <td><b>Colour</b></td> <td>Standard Range</td> </tr> <tr> <td><b>Gloss level</b></td> <td>Gloss</td> </tr> <tr> <td><b>Volume Solid</b></td> <td>Approx. 85%</td> </tr> <tr> <td><b>Dry Film Thickness</b></td> <td>350-500 microns per coat</td> </tr> <tr> <td><b>Number of Coat</b></td> <td>1</td> </tr> <tr> <td><b>Theoretical Coverage</b></td> <td>1.70 m<sup>2</sup>/ℓ at 500 microns</td> </tr> <tr> <td><b>Temperature Resistance</b></td> <td>Continuous : 93<sup>o</sup>C (dry) Intermittent : 120<sup>o</sup>C(dry)</td> </tr> <tr> <td><b>VOC</b></td> <td><b>130 g/ℓ</b></td> </tr> <tr> <td><b>Flash Point</b></td> <td>Base : 29<sup>o</sup>C Hardener : 27<sup>o</sup>C</td> </tr> <tr> <td><b>Shelf Life</b></td> <td>At least 12 months</td> </tr> <tr> <td><b>Pack Size</b></td> <td></td> </tr> <tr> <td>    20 Kgs unit</td> <td>Base : 16 Kgs , Hardener : 4 Kgs</td> </tr> </table>	<b>Colour</b>	Standard Range	<b>Gloss level</b>	Gloss	<b>Volume Solid</b>	Approx. 85%	<b>Dry Film Thickness</b>	350-500 microns per coat	<b>Number of Coat</b>	1	<b>Theoretical Coverage</b>	1.70 m <sup>2</sup> /ℓ at 500 microns	<b>Temperature Resistance</b>	Continuous : 93 <sup>o</sup> C (dry) Intermittent : 120 <sup>o</sup> C(dry)	<b>VOC</b>	<b>130 g/ℓ</b>	<b>Flash Point</b>	Base : 29 <sup>o</sup> C Hardener : 27 <sup>o</sup> C	<b>Shelf Life</b>	At least 12 months	<b>Pack Size</b>		20 Kgs unit	Base : 16 Kgs , Hardener : 4 Kgs												
<b>Colour</b>	Standard Range																																				
<b>Gloss level</b>	Gloss																																				
<b>Volume Solid</b>	Approx. 85%																																				
<b>Dry Film Thickness</b>	350-500 microns per coat																																				
<b>Number of Coat</b>	1																																				
<b>Theoretical Coverage</b>	1.70 m <sup>2</sup> /ℓ at 500 microns																																				
<b>Temperature Resistance</b>	Continuous : 93 <sup>o</sup> C (dry) Intermittent : 120 <sup>o</sup> C(dry)																																				
<b>VOC</b>	<b>130 g/ℓ</b>																																				
<b>Flash Point</b>	Base : 29 <sup>o</sup> C Hardener : 27 <sup>o</sup> C																																				
<b>Shelf Life</b>	At least 12 months																																				
<b>Pack Size</b>																																					
20 Kgs unit	Base : 16 Kgs , Hardener : 4 Kgs																																				
<b>SURFACE PREPARATION</b>	<p><b>Steel</b> Refer to specific instruction for primer coats being used for application. All previous coats must be clean and dry. Old coating system must be roughened, cleaned and dry.</p> <p><b>Concrete</b> Abrasive blast to ASTM D 4259. No primer normally required.</p>																																				
<b>APPLICATION DATA</b>	<table border="0"> <tr> <td colspan="2"><b>Application Methods</b></td> </tr> <tr> <td colspan="2">Airless Spray</td> </tr> <tr> <td>    Nozzle Tip</td> <td>0.46 – 0.58 mm (0.018 – 0.023 inch)</td> </tr> <tr> <td>    Nozzle Pressure</td> <td>10 MPa (approx. 1400 psi)</td> </tr> <tr> <td colspan="2">Conventional Spray</td> </tr> <tr> <td>    Nozzle Tip</td> <td>1.8 – 2.0 mm (0.071 – 0.079 inch)</td> </tr> <tr> <td>    Nozzle Pressure</td> <td>0.3 Mpa (approx. 43 psi)</td> </tr> <tr> <td colspan="2">Brush or Roller Only for touch up and for first coat to concrete surfaces</td> </tr> <tr> <td><b>Mixing Ratio By Volume</b></td> <td>Base : Hardener = 4 : 1</td> </tr> <tr> <td><b>Thinner</b></td> <td>FOXANER 005</td> </tr> <tr> <td><b>Surface Temperature</b></td> <td>Should be 10<sup>o</sup>C – 49<sup>o</sup>C, at least 3<sup>o</sup>C above the dew point to prevent condensation</td> </tr> <tr> <td colspan="2"><b>Drying Time</b></td> </tr> <tr> <td>    Touch Dry</td> <td>4 hours at 25<sup>o</sup>C, 12 hours at 40<sup>o</sup>C</td> </tr> <tr> <td>    Hard Dry</td> <td>8 hours at 25<sup>o</sup>C, 3 hours at 40<sup>o</sup>C</td> </tr> <tr> <td colspan="2">Over coating Interval</td> </tr> <tr> <td>    Minimum</td> <td>10 hours at 25<sup>o</sup>C, 5 hours at 32<sup>o</sup>C</td> </tr> <tr> <td>    Maximum</td> <td>Unlimited (must be roughened)</td> </tr> <tr> <td><b>Pot Life</b></td> <td>1 hour at 25<sup>o</sup>C, 2 hours at 32<sup>o</sup>C</td> </tr> </table>	<b>Application Methods</b>		Airless Spray		Nozzle Tip	0.46 – 0.58 mm (0.018 – 0.023 inch)	Nozzle Pressure	10 MPa (approx. 1400 psi)	Conventional Spray		Nozzle Tip	1.8 – 2.0 mm (0.071 – 0.079 inch)	Nozzle Pressure	0.3 Mpa (approx. 43 psi)	Brush or Roller Only for touch up and for first coat to concrete surfaces		<b>Mixing Ratio By Volume</b>	Base : Hardener = 4 : 1	<b>Thinner</b>	FOXANER 005	<b>Surface Temperature</b>	Should be 10 <sup>o</sup> C – 49 <sup>o</sup> C, at least 3 <sup>o</sup> C above the dew point to prevent condensation	<b>Drying Time</b>		Touch Dry	4 hours at 25 <sup>o</sup> C, 12 hours at 40 <sup>o</sup> C	Hard Dry	8 hours at 25 <sup>o</sup> C, 3 hours at 40 <sup>o</sup> C	Over coating Interval		Minimum	10 hours at 25 <sup>o</sup> C, 5 hours at 32 <sup>o</sup> C	Maximum	Unlimited (must be roughened)	<b>Pot Life</b>	1 hour at 25 <sup>o</sup> C, 2 hours at 32 <sup>o</sup> C
<b>Application Methods</b>																																					
Airless Spray																																					
Nozzle Tip	0.46 – 0.58 mm (0.018 – 0.023 inch)																																				
Nozzle Pressure	10 MPa (approx. 1400 psi)																																				
Conventional Spray																																					
Nozzle Tip	1.8 – 2.0 mm (0.071 – 0.079 inch)																																				
Nozzle Pressure	0.3 Mpa (approx. 43 psi)																																				
Brush or Roller Only for touch up and for first coat to concrete surfaces																																					
<b>Mixing Ratio By Volume</b>	Base : Hardener = 4 : 1																																				
<b>Thinner</b>	FOXANER 005																																				
<b>Surface Temperature</b>	Should be 10 <sup>o</sup> C – 49 <sup>o</sup> C, at least 3 <sup>o</sup> C above the dew point to prevent condensation																																				
<b>Drying Time</b>																																					
Touch Dry	4 hours at 25 <sup>o</sup> C, 12 hours at 40 <sup>o</sup> C																																				
Hard Dry	8 hours at 25 <sup>o</sup> C, 3 hours at 40 <sup>o</sup> C																																				
Over coating Interval																																					
Minimum	10 hours at 25 <sup>o</sup> C, 5 hours at 32 <sup>o</sup> C																																				
Maximum	Unlimited (must be roughened)																																				
<b>Pot Life</b>	1 hour at 25 <sup>o</sup> C, 2 hours at 32 <sup>o</sup> C																																				

**SAFETY PRECAUTION**

*Keep away from heat, spark and Open flames. Avoid breathing of vapour on skin and eye contact. Keep container closed and store in cool, ventilated area when not in use.*

*Proper ventilation and protective measures must be provided during mixing, application and drying, to keep vapour concentration within safe limits and to protect against toxic hazard.*

*Necessary safety equipment must be used and ventilation requirements carefully observed, especially in confined or enclosed spaces, such as tank interior and building.*

---

**DISCLAIMER**

*The information in this product data sheet is given to the best of our knowledge based on laboratory testing and practical experience. If the product is used under condition beyond our control, we cannot guarantee anything but the quality of the products it self. The information in this product data sheet is liable for modification from time to time in the light of experience and our policy of continuous product development, and without further notice.*

**ISSUED: January 2009**