

FOXAPOX-ZP (OX-505)

Epoxy Zinc Phosphate Primer

PRODUCT DESCRIPTION	Polyamide cured inhibitive epoxy primer.																																				
RECOMMENDED USE	Epoxy primer with recommended epoxy Topcoat for the protection of steel in aggressive industrial and marine environments such as structural steel, tank exterior, bridges, chemical plants, food processing installations.																																				
CHARACTERISTICS	<ul style="list-style-type: none"> • Pigmented with zinc phosphate, free of lead and chrome pigment. • Tough epoxy film reduces cost of site touch-up by minimizing handling and erection damage. • Fast drying, may be top coated in 3 hours at 25^oC. • Good abrasion resistance which minimises mechanical damage. • Resists weathering without a Topcoat for extended period (6 months maximum). • Ideal as a shopprimer. 																																				
PHYSICAL DATA	<table border="0"> <tr> <td>Colour</td> <td>White and Red</td> </tr> <tr> <td>Gloss Level</td> <td>Flat</td> </tr> <tr> <td>Volume Solid</td> <td>Approx. 49%</td> </tr> <tr> <td>Dry Film Thickness</td> <td>50 microns per coat</td> </tr> <tr> <td>Number of Coat</td> <td>1</td> </tr> <tr> <td>Theoretical Coverage</td> <td>9.80 sq.m/ for 50 microns</td> </tr> <tr> <td>Temperature Resistance</td> <td>Continuous : 85^oC (dry) Intermittent : 123^oC (dry)</td> </tr> <tr> <td>VOC</td> <td>422 g/</td> </tr> <tr> <td>Flash Point</td> <td>Base : 47^oC Hardener : 28^oC</td> </tr> <tr> <td>Shelf Life</td> <td>At least 12 months</td> </tr> <tr> <td>Pack Size</td> <td>20 Kgs unit</td> </tr> <tr> <td></td> <td>Base : 16 Kgs , Hardener : 4 Kgs</td> </tr> </table>	Colour	White and Red	Gloss Level	Flat	Volume Solid	Approx. 49%	Dry Film Thickness	50 microns per coat	Number of Coat	1	Theoretical Coverage	9.80 sq.m/ for 50 microns	Temperature Resistance	Continuous : 85 ^o C (dry) Intermittent : 123 ^o C (dry)	VOC	422 g/	Flash Point	Base : 47 ^o C Hardener : 28 ^o C	Shelf Life	At least 12 months	Pack Size	20 Kgs unit		Base : 16 Kgs , Hardener : 4 Kgs												
Colour	White and Red																																				
Gloss Level	Flat																																				
Volume Solid	Approx. 49%																																				
Dry Film Thickness	50 microns per coat																																				
Number of Coat	1																																				
Theoretical Coverage	9.80 sq.m/ for 50 microns																																				
Temperature Resistance	Continuous : 85 ^o C (dry) Intermittent : 123 ^o C (dry)																																				
VOC	422 g/																																				
Flash Point	Base : 47 ^o C Hardener : 28 ^o C																																				
Shelf Life	At least 12 months																																				
Pack Size	20 Kgs unit																																				
	Base : 16 Kgs , Hardener : 4 Kgs																																				
SURFACE PREPARATION	Dry abrasive blast in accordance with ISO – Sa 2.5 or SSPC – SP 10 “Near White”. Blast to achieve an anchor profile of 25 – 50 microns as determined with a Keane Tator Surface Profile Comparator. Remove abrasive residue or dust from surface.																																				
APPLICATION DATA	<table border="0"> <tr> <td colspan="2">Application Methods</td> </tr> <tr> <td>Airless Spray</td> <td></td> </tr> <tr> <td> Nozzle Tip</td> <td>0.46 – 0.58 mm (0.018 – 0.023 inch)</td> </tr> <tr> <td> Nozzle Pressure</td> <td>10 MPa (approx. 1400 psi)</td> </tr> <tr> <td>Conventional Spray</td> <td></td> </tr> <tr> <td> Nozzle Tip</td> <td>1.8 – 2.0 mm (0.071 – 0.079 inch)</td> </tr> <tr> <td> Nozzle Pressure</td> <td>0.3 MPa (approx. 43 psi)</td> </tr> <tr> <td>Mixing Ratio By Volume</td> <td>Base : Hardener = 4 : 1</td> </tr> <tr> <td>Thinner</td> <td>FOXANER 005</td> </tr> <tr> <td>Surface Temperature</td> <td>Should be 10^oC – 49^oC, at least 3^oC above the dew point to prevent condensation</td> </tr> <tr> <td colspan="2">Drying Time</td> </tr> <tr> <td> Touch Dry</td> <td>2 hours at 25^oC, 1 hour at 32^oC</td> </tr> <tr> <td> Through Dry</td> <td>4 hours at 25^oC, 2 hours at 32^oC</td> </tr> <tr> <td> To Topcoat</td> <td></td> </tr> <tr> <td> Minimum</td> <td>4 hours at 25^oC, 2 hours at 32^oC</td> </tr> <tr> <td> Maximum</td> <td>6 months (roughened and dry)</td> </tr> <tr> <td> Full Cure</td> <td>7 days</td> </tr> <tr> <td>Pot Life</td> <td>8 hours at 25^oC, 4 hours at 32^oC</td> </tr> </table>	Application Methods		Airless Spray		Nozzle Tip	0.46 – 0.58 mm (0.018 – 0.023 inch)	Nozzle Pressure	10 MPa (approx. 1400 psi)	Conventional Spray		Nozzle Tip	1.8 – 2.0 mm (0.071 – 0.079 inch)	Nozzle Pressure	0.3 MPa (approx. 43 psi)	Mixing Ratio By Volume	Base : Hardener = 4 : 1	Thinner	FOXANER 005	Surface Temperature	Should be 10 ^o C – 49 ^o C, at least 3 ^o C above the dew point to prevent condensation	Drying Time		Touch Dry	2 hours at 25 ^o C, 1 hour at 32 ^o C	Through Dry	4 hours at 25 ^o C, 2 hours at 32 ^o C	To Topcoat		Minimum	4 hours at 25 ^o C, 2 hours at 32 ^o C	Maximum	6 months (roughened and dry)	Full Cure	7 days	Pot Life	8 hours at 25 ^o C, 4 hours at 32 ^o C
Application Methods																																					
Airless Spray																																					
Nozzle Tip	0.46 – 0.58 mm (0.018 – 0.023 inch)																																				
Nozzle Pressure	10 MPa (approx. 1400 psi)																																				
Conventional Spray																																					
Nozzle Tip	1.8 – 2.0 mm (0.071 – 0.079 inch)																																				
Nozzle Pressure	0.3 MPa (approx. 43 psi)																																				
Mixing Ratio By Volume	Base : Hardener = 4 : 1																																				
Thinner	FOXANER 005																																				
Surface Temperature	Should be 10 ^o C – 49 ^o C, at least 3 ^o C above the dew point to prevent condensation																																				
Drying Time																																					
Touch Dry	2 hours at 25 ^o C, 1 hour at 32 ^o C																																				
Through Dry	4 hours at 25 ^o C, 2 hours at 32 ^o C																																				
To Topcoat																																					
Minimum	4 hours at 25 ^o C, 2 hours at 32 ^o C																																				
Maximum	6 months (roughened and dry)																																				
Full Cure	7 days																																				
Pot Life	8 hours at 25 ^o C, 4 hours at 32 ^o C																																				

SAFETY PRECAUTION

Keep away from heat, spark and Open flames. Avoid breathing of vapour on skin and eye contact. Keep container closed and store in cool, ventilated area when not in use. Proper ventilation and protective measures must be provided during mixing, application and drying, to keep vapour concentration within safe limits and to protect against toxic hazard.

Necessary safety equipment must be used and ventilation requirements carefully observed, especially in confined or enclosed spaces, such as tank interior and building.

DISCLAIMER

The information in this product data sheet is given to the best of our knowledge based on laboratory testing and practical experience. If the product is used under condition beyond our control, we cannot guarantee anything but the quality of the products it self. The information in this product data sheet is liable for modification from time to time in the light of experience and our policy of continuous product development, and without further notice.

ISSUED: January 2009