

Product Data Sheet

FOXAPOX LINING (OX-509DS)

Modified Epoxy

PRODUCT DESCRIPTION	High solid cured epoxy.																																				
RECOMMENDED USE	Tank lining, interior of steel tanks, pipelines, hopper cars and splash zone on damp/ wet surfaces..																																				
CHARACTERISTICS	<ul style="list-style-type: none"> • Tank coating with good chemical resistance against a wide range of chemicals • Good immersion resistant to water, fuel and a wide range of chemicals. • Resistant to salt and fresh water. • Highly abrasion and impact resistant. 																																				
PHYSICAL DATA	<table> <tr> <td>Colour</td> <td>Available On Request</td> </tr> <tr> <td>Gloss Level</td> <td>Satin</td> </tr> <tr> <td>Volume Solid</td> <td>Approx. 90%</td> </tr> <tr> <td>Dry Film Thickness</td> <td>125 microns per coat</td> </tr> <tr> <td>Number of Coat</td> <td>2</td> </tr> <tr> <td>Theoretical Coverage</td> <td>6.4 sq.m/ℓ for 125 microns</td> </tr> <tr> <td>Temperature Resistance</td> <td>Continuous : 95⁰C (dry), 50⁰C (wet)</td> </tr> <tr> <td>VOC</td> <td>108 g/ℓ</td> </tr> <tr> <td>Flash Point</td> <td>Base: 42⁰C Hardener: 56⁰C</td> </tr> <tr> <td>Shelf Life</td> <td>At least 12 months</td> </tr> </table>	Colour	Available On Request	Gloss Level	Satin	Volume Solid	Approx. 90%	Dry Film Thickness	125 microns per coat	Number of Coat	2	Theoretical Coverage	6.4 sq.m/ℓ for 125 microns	Temperature Resistance	Continuous : 95 ⁰ C (dry), 50 ⁰ C (wet)	VOC	108 g/ℓ	Flash Point	Base: 42 ⁰ C Hardener: 56 ⁰ C	Shelf Life	At least 12 months																
Colour	Available On Request																																				
Gloss Level	Satin																																				
Volume Solid	Approx. 90%																																				
Dry Film Thickness	125 microns per coat																																				
Number of Coat	2																																				
Theoretical Coverage	6.4 sq.m/ℓ for 125 microns																																				
Temperature Resistance	Continuous : 95 ⁰ C (dry), 50 ⁰ C (wet)																																				
VOC	108 g/ℓ																																				
Flash Point	Base: 42 ⁰ C Hardener: 56 ⁰ C																																				
Shelf Life	At least 12 months																																				
SURFACE PREPARATION	<p>Steel Dry abrasive blast in accordance with ISO – Sa 2.5 or SSPC – SP 10 “Near White”. Blast to achieve a 25 – 50 microns anchor profile of as indicate with a Keane Tator Surface Profile Comparator. Remove abrasive residue or dust from surface.</p>																																				
APPLICATION DATA	<table> <tr> <td colspan="2">Application Methods</td> </tr> <tr> <td colspan="2">Airless Spray</td> </tr> <tr> <td> Nozzle Tip</td> <td>0.46 – 0.58 mm (0.018 – 0.023 inch)</td> </tr> <tr> <td> Nozzle Pressure</td> <td>10 MPa (approx. 1400 psi)</td> </tr> <tr> <td colspan="2">Conventional Spray</td> </tr> <tr> <td> Nozzle Tip</td> <td>1.8 – 2.0 mm (0.071 – 0.079 inch)</td> </tr> <tr> <td> Nozzle Pressure</td> <td>0.3 MPa (approx. 43 psi)</td> </tr> <tr> <td>Mixing Ratio By Volume</td> <td>Base : Hardener = 4 : 1</td> </tr> <tr> <td>Thinner</td> <td>FOXANER 005</td> </tr> <tr> <td>Surface Temperature</td> <td>Should be 10⁰C – 49⁰C, at least 3⁰C above the dew point to prevent condensation</td> </tr> <tr> <td colspan="2">Drying Time</td> </tr> <tr> <td> Touch Dry</td> <td>3 hours at 25⁰C, 1.5 hours at 32⁰C</td> </tr> <tr> <td> Through Dry</td> <td>24 hours at 25⁰C, 13 hours at 32⁰C</td> </tr> <tr> <td> To Recoat</td> <td></td> </tr> <tr> <td> Minimum</td> <td>16 hours at 25⁰C, 8 hours at 32⁰C</td> </tr> <tr> <td> Maximum</td> <td>3 weeks</td> </tr> <tr> <td> Full Cure</td> <td>7 days (under ventilated conditions)</td> </tr> <tr> <td>Pot Life</td> <td>10 hours at 25⁰C, 5 hours at 32⁰C</td> </tr> </table>	Application Methods		Airless Spray		Nozzle Tip	0.46 – 0.58 mm (0.018 – 0.023 inch)	Nozzle Pressure	10 MPa (approx. 1400 psi)	Conventional Spray		Nozzle Tip	1.8 – 2.0 mm (0.071 – 0.079 inch)	Nozzle Pressure	0.3 MPa (approx. 43 psi)	Mixing Ratio By Volume	Base : Hardener = 4 : 1	Thinner	FOXANER 005	Surface Temperature	Should be 10 ⁰ C – 49 ⁰ C, at least 3 ⁰ C above the dew point to prevent condensation	Drying Time		Touch Dry	3 hours at 25 ⁰ C, 1.5 hours at 32 ⁰ C	Through Dry	24 hours at 25 ⁰ C, 13 hours at 32 ⁰ C	To Recoat		Minimum	16 hours at 25 ⁰ C, 8 hours at 32 ⁰ C	Maximum	3 weeks	Full Cure	7 days (under ventilated conditions)	Pot Life	10 hours at 25 ⁰ C, 5 hours at 32 ⁰ C
Application Methods																																					
Airless Spray																																					
Nozzle Tip	0.46 – 0.58 mm (0.018 – 0.023 inch)																																				
Nozzle Pressure	10 MPa (approx. 1400 psi)																																				
Conventional Spray																																					
Nozzle Tip	1.8 – 2.0 mm (0.071 – 0.079 inch)																																				
Nozzle Pressure	0.3 MPa (approx. 43 psi)																																				
Mixing Ratio By Volume	Base : Hardener = 4 : 1																																				
Thinner	FOXANER 005																																				
Surface Temperature	Should be 10 ⁰ C – 49 ⁰ C, at least 3 ⁰ C above the dew point to prevent condensation																																				
Drying Time																																					
Touch Dry	3 hours at 25 ⁰ C, 1.5 hours at 32 ⁰ C																																				
Through Dry	24 hours at 25 ⁰ C, 13 hours at 32 ⁰ C																																				
To Recoat																																					
Minimum	16 hours at 25 ⁰ C, 8 hours at 32 ⁰ C																																				
Maximum	3 weeks																																				
Full Cure	7 days (under ventilated conditions)																																				
Pot Life	10 hours at 25 ⁰ C, 5 hours at 32 ⁰ C																																				
SAFETY PRECAUTION	<p><i>Keep away from heat, spark and Open flames. Avoid breathing of vapour on skin and eye contact. Keep container closed and store in cool, ventilated area when not in use. Proper ventilation and protective measures must be provided during mixing, application and drying, to keep vapour concentration within safe limits and to protect against topic hazard. Necessary safety equipment must be used and ventilation requirements carefully observed, especially in confined or enclosed spaces, such as tank interior and building.</i></p>																																				

DISCLAIMER

The information in this product data sheet is given to the best of our knowledge based on laboratory testing and practical experience. If the product is used under condition beyond our control, we cannot guarantee anything but the quality of the products it self. The information in this product data sheet is liable for modification from time to time in the light of experience and our policy of continuous product development, and without further notice.

ISSUED: January 2009