

FOXAPOX MULTI (OX-510)

Multi Purpose Epoxy

PRODUCT DESCRIPTION	Multi purpose high build polyamine cured epoxy.																										
RECOMMENDED USE	High performance primer or built coat for durable systems with wide range of protective topcoat.																										
CHARACTERISTICS	<ul style="list-style-type: none"> • Rust inhibitive epoxy primer. • Compatible with compromised surface preparation. • Excellent shop primer for corrosive service. • Suitable for hand or power tool prepared steel surface with rust • Excellent adhesion to bare steel and inorganic zinc silicate. • Tank lining for alkaline, salt solution, petroleum fuels and sewage waste. • Can be applied over concrete, aluminium, stainless steel and galvanizing. 																										
PHYSICAL DATA	<table border="0"> <tr> <td>Colour</td> <td>Available On Request</td> </tr> <tr> <td>Gloss Level</td> <td>Flat</td> </tr> <tr> <td>Volume Solid</td> <td>Approx. 73%</td> </tr> <tr> <td>Dry Film Thickness</td> <td>100 – 150 microns per coat</td> </tr> <tr> <td>Number of Coat</td> <td>1 or 2</td> </tr> <tr> <td>Theoretical Coverage</td> <td>7.00 sq.m/ℓ for 100 microns</td> </tr> <tr> <td>Density</td> <td>1.4 kg/ℓ</td> </tr> <tr> <td>Temperature Resistance</td> <td>Continuous : 93°C (dry) , 60°C (wet) Intermittent : 120°C (dry) , 80°C (wet)</td> </tr> <tr> <td>VOC</td> <td>276 g/ℓ</td> </tr> <tr> <td>Flash Point</td> <td>Base : 53°C Hardener : 48°C</td> </tr> <tr> <td>Shelf Life</td> <td>At least 12 months</td> </tr> <tr> <td>Pack Size</td> <td>20 Kgs unit</td> </tr> <tr> <td></td> <td>Base : 10 Kgs , Hardener : 10 Kgs</td> </tr> </table>	Colour	Available On Request	Gloss Level	Flat	Volume Solid	Approx. 73%	Dry Film Thickness	100 – 150 microns per coat	Number of Coat	1 or 2	Theoretical Coverage	7.00 sq.m/ℓ for 100 microns	Density	1.4 kg/ℓ	Temperature Resistance	Continuous : 93°C (dry) , 60°C (wet) Intermittent : 120°C (dry) , 80°C (wet)	VOC	276 g/ℓ	Flash Point	Base : 53°C Hardener : 48°C	Shelf Life	At least 12 months	Pack Size	20 Kgs unit		Base : 10 Kgs , Hardener : 10 Kgs
Colour	Available On Request																										
Gloss Level	Flat																										
Volume Solid	Approx. 73%																										
Dry Film Thickness	100 – 150 microns per coat																										
Number of Coat	1 or 2																										
Theoretical Coverage	7.00 sq.m/ℓ for 100 microns																										
Density	1.4 kg/ℓ																										
Temperature Resistance	Continuous : 93°C (dry) , 60°C (wet) Intermittent : 120°C (dry) , 80°C (wet)																										
VOC	276 g/ℓ																										
Flash Point	Base : 53°C Hardener : 48°C																										
Shelf Life	At least 12 months																										
Pack Size	20 Kgs unit																										
	Base : 10 Kgs , Hardener : 10 Kgs																										
SURFACE PREPARATION	<p>Steel Dry abrasive blast in accordance with ISO – Sa 2.5 or SSPC – SP 10 “Near White”. Blast to achieve an anchor profile of 25 – 50 microns as determined with a Keane Tator Surface Profile Comparator. Remove abrasive residue or dust from surface.</p> <p>Concrete Abrasive blast to ASTM D 4259. Surface must be free of moisture, grease and other contaminants.</p> <p>Aluminium and Galvanizing Remove oil, grease with neutral detergent, or blast lightly with fine abrasive, priming or etching with FOXAPOXY ETCH.</p> <p>Aged Coating Free of all loose paint, chalky residue. Roughened or clean by pressure water blast (minimum 1000 psi), cleaned and dry.</p>																										
APPLICATION DATA	<table border="0"> <tr> <td colspan="2">Application Methods</td> </tr> <tr> <td colspan="2">Airless Spray</td> </tr> <tr> <td> Nozzle Tip</td> <td>0.46 – 0.56 mm (0.018 – 0.023 inch)</td> </tr> <tr> <td> Nozzle Pressure</td> <td>10 MPa (approx. 1400 psi)</td> </tr> <tr> <td colspan="2">Conventional Spray</td> </tr> <tr> <td> Nozzle Tip</td> <td>1.8 – 2.0 mm (0.071 – 0.079 inch)</td> </tr> <tr> <td> Nozzle Pressure</td> <td>0.3 MPa (approx. 43 psi)</td> </tr> <tr> <td>Mixing Ratio By Volume</td> <td>Base : Hardener = 1 : 1</td> </tr> <tr> <td>Thinner</td> <td>FOXANER 005</td> </tr> </table>	Application Methods		Airless Spray		Nozzle Tip	0.46 – 0.56 mm (0.018 – 0.023 inch)	Nozzle Pressure	10 MPa (approx. 1400 psi)	Conventional Spray		Nozzle Tip	1.8 – 2.0 mm (0.071 – 0.079 inch)	Nozzle Pressure	0.3 MPa (approx. 43 psi)	Mixing Ratio By Volume	Base : Hardener = 1 : 1	Thinner	FOXANER 005								
Application Methods																											
Airless Spray																											
Nozzle Tip	0.46 – 0.56 mm (0.018 – 0.023 inch)																										
Nozzle Pressure	10 MPa (approx. 1400 psi)																										
Conventional Spray																											
Nozzle Tip	1.8 – 2.0 mm (0.071 – 0.079 inch)																										
Nozzle Pressure	0.3 MPa (approx. 43 psi)																										
Mixing Ratio By Volume	Base : Hardener = 1 : 1																										
Thinner	FOXANER 005																										

Surface Temperature	Should be 10°C – 49°C, at least 3°C above the dew point to prevent condensation
Drying Time	
Touch Dry	2 hours at 25°C, 1 hour at 32°C
Through Dry	14 hours at 25°C, 8 hours at 32°C
To Topcoat	
Minimum	7 hours at 25°C, 4 hours at 32°C
Maximum	1 month (roughened, clean and dry)
Full Cure	7 days
Pot Life	3 hours at 25°C, 1.5 hours at 32°C

SAFETY PRECAUTION

Keep away from heat, spark and Open flames. Avoid breathing of vapour on skin and eye contact. Keep container closed and store in cool, ventilated area when not in use. Proper ventilation and protective measures must be provided during mixing, application and drying, to keep vapour concentration within safe limits and to protect against toxic hazard.

Necessary safety equipment must be used and ventilation requirements carefully observed, especially in confined or enclosed spaces, such as tank interior and building.

DISCLAIMER

The information in this product data sheet is given to the best of our knowledge based on laboratory testing and practical experience. If the product is used under condition beyond our control, we cannot guarantee anything but the quality of the products it self. The information in this product data sheet is liable for modification from time to time in the light of experience and our policy of continuous product development, and without further notice.

ISSUED: **January 2020**