

FOXAPOX-PRIME (OX-515)

Polyamide Epoxy

PRODUCT DESCRIPTION	A High Build Epoxy																																								
RECOMMENDED USE	Epoxy High Build for general maintenance coating which can be applied to new or old steel and resists to splash / spillage of a wide range of chemicals.																																								
CHARACTERISTICS	<ul style="list-style-type: none"> • Excellent corrosion resistance and good flexibility. • High performance self-priming topcoat.. • Resist continuous immersion in petroleum products such as motor fuels, jet fuels, diesel oil and gasoline. • Compatible with various aged coatings. • Resist Continuous immersion in salt solution, fresh or demineralised water. 																																								
PHYSICAL DATA	<table border="0"> <tr> <td>Colour</td> <td>Availabel On Request</td> </tr> <tr> <td>Finish</td> <td>Doff/ Satin</td> </tr> <tr> <td>Volume Solid</td> <td>Approx. 78%</td> </tr> <tr> <td>Dry Film Thickness</td> <td>125 microns per coat</td> </tr> <tr> <td>Number of Coat</td> <td>2 - 3</td> </tr> <tr> <td>Theoretical Coverage</td> <td>4.96 sq.m/ℓ for 125 microns</td> </tr> <tr> <td>Density</td> <td>1.32 kg/ℓ</td> </tr> <tr> <td>Temperature Resistance</td> <td>Maximum : °C (dry)</td> </tr> <tr> <td>VOC</td> <td>307 g/ℓ</td> </tr> <tr> <td>Flash Point</td> <td>Base : 24°C Hardener : 40°C</td> </tr> <tr> <td>Shelf Life</td> <td>At least 12 months</td> </tr> <tr> <td>Pack Size</td> <td></td> </tr> <tr> <td style="padding-left: 20px;">20 Kgs unit</td> <td>Base : 16 Kgs , Hardener : 4 Kgs</td> </tr> </table>	Colour	Availabel On Request	Finish	Doff/ Satin	Volume Solid	Approx. 78%	Dry Film Thickness	125 microns per coat	Number of Coat	2 - 3	Theoretical Coverage	4.96 sq.m/ℓ for 125 microns	Density	1.32 kg/ℓ	Temperature Resistance	Maximum : °C (dry)	VOC	307 g/ℓ	Flash Point	Base : 24°C Hardener : 40°C	Shelf Life	At least 12 months	Pack Size		20 Kgs unit	Base : 16 Kgs , Hardener : 4 Kgs														
Colour	Availabel On Request																																								
Finish	Doff/ Satin																																								
Volume Solid	Approx. 78%																																								
Dry Film Thickness	125 microns per coat																																								
Number of Coat	2 - 3																																								
Theoretical Coverage	4.96 sq.m/ℓ for 125 microns																																								
Density	1.32 kg/ℓ																																								
Temperature Resistance	Maximum : °C (dry)																																								
VOC	307 g/ℓ																																								
Flash Point	Base : 24°C Hardener : 40°C																																								
Shelf Life	At least 12 months																																								
Pack Size																																									
20 Kgs unit	Base : 16 Kgs , Hardener : 4 Kgs																																								
SURFACE PREPARATION	Dry abrasive blast in accordance with ISO – Sa 2.5 or SSPC – SP 10 “Near White”. Remove abrasive residue or dust from surface.																																								
APPLICATION DATA	<table border="0"> <tr> <td colspan="2">Application Methods</td> </tr> <tr> <td colspan="2">Airless Spray</td> </tr> <tr> <td style="padding-left: 20px;">Nozzle Tip</td> <td>Approx. 0.46 mm (0.018 inch)</td> </tr> <tr> <td style="padding-left: 20px;">Nozzle Pressure</td> <td>10 MPa (approx. 1400 psi)</td> </tr> <tr> <td colspan="2">Conventional Spray</td> </tr> <tr> <td style="padding-left: 20px;">Nozzle Tip</td> <td>Approx. 1.8 mm (0.071 inch)</td> </tr> <tr> <td style="padding-left: 20px;">Nozzle Pressure</td> <td>0.3 MPa (approx. 43 psi)</td> </tr> <tr> <td style="padding-left: 20px;">Brush or Roller</td> <td>Can be applied by brush or roller but may require several coats to achieve the same film thickness</td> </tr> <tr> <td colspan="2">Mixing Ratio By Volume</td> </tr> <tr> <td colspan="2">Base : Hardener = 4 : 1</td> </tr> <tr> <td colspan="2">Thinner</td> </tr> <tr> <td colspan="2">FOXANER 005</td> </tr> <tr> <td colspan="2">Surface Temperature</td> </tr> <tr> <td colspan="2">Should be 10°C – 49°C, at least 3°C above the dew point to prevent condensation</td> </tr> <tr> <td colspan="2">Drying Time</td> </tr> <tr> <td style="padding-left: 20px;">Touch Dry</td> <td>2 hours at 25°C, 1 hour at 32°C</td> </tr> <tr> <td style="padding-left: 20px;">Through Dry</td> <td>14 hours at 25°C, 7 hours at 32°C</td> </tr> <tr> <td style="padding-left: 20px;">Recoat Time</td> <td>10 hours at 25°C, 5 hours at 32°C</td> </tr> <tr> <td style="padding-left: 20px;">Curing Time</td> <td>9 days (under ventilated conditions</td> </tr> <tr> <td style="padding-left: 20px;">Pot Life</td> <td>8 hours at 25°C, 4 hours at 32°C</td> </tr> </table>	Application Methods		Airless Spray		Nozzle Tip	Approx. 0.46 mm (0.018 inch)	Nozzle Pressure	10 MPa (approx. 1400 psi)	Conventional Spray		Nozzle Tip	Approx. 1.8 mm (0.071 inch)	Nozzle Pressure	0.3 MPa (approx. 43 psi)	Brush or Roller	Can be applied by brush or roller but may require several coats to achieve the same film thickness	Mixing Ratio By Volume		Base : Hardener = 4 : 1		Thinner		FOXANER 005		Surface Temperature		Should be 10°C – 49°C, at least 3°C above the dew point to prevent condensation		Drying Time		Touch Dry	2 hours at 25°C, 1 hour at 32°C	Through Dry	14 hours at 25°C, 7 hours at 32°C	Recoat Time	10 hours at 25°C, 5 hours at 32°C	Curing Time	9 days (under ventilated conditions	Pot Life	8 hours at 25°C, 4 hours at 32°C
Application Methods																																									
Airless Spray																																									
Nozzle Tip	Approx. 0.46 mm (0.018 inch)																																								
Nozzle Pressure	10 MPa (approx. 1400 psi)																																								
Conventional Spray																																									
Nozzle Tip	Approx. 1.8 mm (0.071 inch)																																								
Nozzle Pressure	0.3 MPa (approx. 43 psi)																																								
Brush or Roller	Can be applied by brush or roller but may require several coats to achieve the same film thickness																																								
Mixing Ratio By Volume																																									
Base : Hardener = 4 : 1																																									
Thinner																																									
FOXANER 005																																									
Surface Temperature																																									
Should be 10°C – 49°C, at least 3°C above the dew point to prevent condensation																																									
Drying Time																																									
Touch Dry	2 hours at 25°C, 1 hour at 32°C																																								
Through Dry	14 hours at 25°C, 7 hours at 32°C																																								
Recoat Time	10 hours at 25°C, 5 hours at 32°C																																								
Curing Time	9 days (under ventilated conditions																																								
Pot Life	8 hours at 25°C, 4 hours at 32°C																																								