

FOXAKYD QD (OX-605)

Alkyd Quick Dry

PRODUCT DESCRIPTION	A single component alkyd fast dry																																
RECOMMENDED USE	A gloss finish coat for mild industrial and marine service, for steel work in non-aggressive environment.																																
CHARACTERISTICS	<ul style="list-style-type: none"> • Easily applied by spray, brush or roller. • Good gloss retention, even in industrial environment. • Excellent maintenance coating, compatible with a wide range of primer and existing coated surface. 																																
PHYSICAL DATA	<table border="0"> <tr> <td>Colour</td> <td>Available on request</td> </tr> <tr> <td>Gloss level</td> <td>Gloss</td> </tr> <tr> <td>Volume Solid</td> <td>Approx. 53%</td> </tr> <tr> <td>Dry Film Thickness</td> <td>40 microns per coat</td> </tr> <tr> <td>Number of Coat</td> <td>1-2</td> </tr> <tr> <td>Theoretical Coverage</td> <td>13.20 sq. m/ℓ for 40 microns</td> </tr> <tr> <td>Density</td> <td>1 kg/ℓ</td> </tr> <tr> <td>Temperature Resistance</td> <td>Continuous : 90°C (dry) Intermittent : 115°C (dry)</td> </tr> <tr> <td>VOC</td> <td>237 g/ℓ</td> </tr> <tr> <td>Flash Point</td> <td>38°C</td> </tr> <tr> <td>Shelf Life</td> <td>At least 12 months</td> </tr> <tr> <td>Pack Size</td> <td>20 Kgs</td> </tr> </table>	Colour	Available on request	Gloss level	Gloss	Volume Solid	Approx. 53%	Dry Film Thickness	40 microns per coat	Number of Coat	1-2	Theoretical Coverage	13.20 sq. m/ℓ for 40 microns	Density	1 kg/ℓ	Temperature Resistance	Continuous : 90°C (dry) Intermittent : 115°C (dry)	VOC	237 g/ℓ	Flash Point	38°C	Shelf Life	At least 12 months	Pack Size	20 Kgs								
Colour	Available on request																																
Gloss level	Gloss																																
Volume Solid	Approx. 53%																																
Dry Film Thickness	40 microns per coat																																
Number of Coat	1-2																																
Theoretical Coverage	13.20 sq. m/ℓ for 40 microns																																
Density	1 kg/ℓ																																
Temperature Resistance	Continuous : 90°C (dry) Intermittent : 115°C (dry)																																
VOC	237 g/ℓ																																
Flash Point	38°C																																
Shelf Life	At least 12 months																																
Pack Size	20 Kgs																																
SURFACE PREPARATION	<p>Steel</p> <p>Dry abrasive blast to minimum ISO – Sa 2 or SSPC – SP 6 “Commercial”. Blast to achieve a 25 microns anchor profile as indicated with a Keane Tator Surface Profile Comparator. Remove abrasive residue or dust from surface. For aged coating, all intact coatings must be clean, dry and free of all contaminants, sufficiently roughened.</p>																																
APPLICATION DATA	<table border="0"> <tr> <td colspan="2">Application Methods</td> </tr> <tr> <td>Airless Spray</td> <td></td> </tr> <tr> <td> Nozzle Tip</td> <td>Approx. 0.28 mm (0.011 inch)</td> </tr> <tr> <td> Nozzle Pressure</td> <td>10 MPa (approx. 1400 psi)</td> </tr> <tr> <td>Conventional Spray</td> <td></td> </tr> <tr> <td> Nozzle Tip</td> <td>1.8 – 2.0 mm (0.071 – 0.079 inch)</td> </tr> <tr> <td> Nozzle Pressure</td> <td>0.3 MPa (approx. 43 psi)</td> </tr> <tr> <td> Brush or roller</td> <td>Recommended</td> </tr> <tr> <td>Thinner</td> <td>FOXANNER 006 (15 - 20%)</td> </tr> <tr> <td>Surface Temperature</td> <td>Should be 10°C – 49°C, at least 3°C above the dew point to prevent condensation</td> </tr> <tr> <td colspan="2">Drying Time</td> </tr> <tr> <td> Touch Dry</td> <td>1 hours at 25°C, 1/2 hour at 32°C</td> </tr> <tr> <td> Through Dry</td> <td>4 hours at 25°C, 2 hours at 32°C</td> </tr> <tr> <td> Over coating</td> <td></td> </tr> <tr> <td> Minimum</td> <td>8 hours</td> </tr> <tr> <td> Maximum</td> <td>Unlimited</td> </tr> </table>	Application Methods		Airless Spray		Nozzle Tip	Approx. 0.28 mm (0.011 inch)	Nozzle Pressure	10 MPa (approx. 1400 psi)	Conventional Spray		Nozzle Tip	1.8 – 2.0 mm (0.071 – 0.079 inch)	Nozzle Pressure	0.3 MPa (approx. 43 psi)	Brush or roller	Recommended	Thinner	FOXANNER 006 (15 - 20%)	Surface Temperature	Should be 10°C – 49°C, at least 3°C above the dew point to prevent condensation	Drying Time		Touch Dry	1 hours at 25°C, 1/2 hour at 32°C	Through Dry	4 hours at 25°C, 2 hours at 32°C	Over coating		Minimum	8 hours	Maximum	Unlimited
Application Methods																																	
Airless Spray																																	
Nozzle Tip	Approx. 0.28 mm (0.011 inch)																																
Nozzle Pressure	10 MPa (approx. 1400 psi)																																
Conventional Spray																																	
Nozzle Tip	1.8 – 2.0 mm (0.071 – 0.079 inch)																																
Nozzle Pressure	0.3 MPa (approx. 43 psi)																																
Brush or roller	Recommended																																
Thinner	FOXANNER 006 (15 - 20%)																																
Surface Temperature	Should be 10°C – 49°C, at least 3°C above the dew point to prevent condensation																																
Drying Time																																	
Touch Dry	1 hours at 25°C, 1/2 hour at 32°C																																
Through Dry	4 hours at 25°C, 2 hours at 32°C																																
Over coating																																	
Minimum	8 hours																																
Maximum	Unlimited																																
SAFETY PRECAUTION	<p><i>Keep away from heat, spark and Open flames. Avoid breathing of vapour on skin and eye contact. Keep container closed and store in cool, ventilated area when not in use.</i></p> <p><i>Proper ventilation and protective measures must be provided during mixing, application and drying, to keep vapour concentration within safe limits and to protect against toxic hazard.</i></p> <p><i>Necessary safety equipment must be used and ventilation requirements carefully observed, especially in confined or enclosed spaces, such as tank interior and building.</i></p>																																
DISCLAIMER	<p><i>The information in this product data sheet is given to the best of our knowledge based on laboratory testing and practical experience. If the product is used under condition beyond our control, we cannot guarantee anything but the quality of the products it self. The information in this product data sheet is liable for modification from time to time in the light of experience and our policy of continuous product development, and without further notice.</i></p>																																