

FOXAFLOOR PRIMER (OX-902)

Epoxy Polyamide Primer

PRODUCT DESCRIPTION	Two packs high solid epoxy polyamide primer.																																																
RECOMMENDED USE	High performance primer and sealing concrete surfaces.																																																
CHARACTERISTICS	<ul style="list-style-type: none"> • Good abrasion resistance. • Excellent impact resistance. • Moisture – tolerance. • Good penetration capabilities. 																																																
PHYSICAL DATA	<table border="0"> <tr> <td style="padding-right: 20px;">Colour</td> <td>Available On Request</td> </tr> <tr> <td>Gloss Level</td> <td>Flat</td> </tr> <tr> <td>Volume Solid</td> <td>58%</td> </tr> <tr> <td>Dry Film Thickness</td> <td>100 – 150 microns</td> </tr> <tr> <td>Number of Coat</td> <td>1 or 2</td> </tr> <tr> <td>Theoretical Coverage</td> <td>4.60 sq.m/ℓ for 125 microns</td> </tr> <tr> <td>Mixing Ratio</td> <td>Base : Hardener = 4 : 1</td> </tr> <tr> <td>Thinner</td> <td>FOXANER 009</td> </tr> <tr> <td>Pack Size</td> <td>20 litres</td> </tr> <tr> <td>Shelf Life</td> <td>12 months</td> </tr> <tr> <td>Pot Life</td> <td>1.5 hours at 32^oC</td> </tr> <tr> <td>Temperature Resistance</td> <td>93^oC (dry)</td> </tr> <tr> <td>Flash Point</td> <td>Base : 25^oC Hardener : 45^oC</td> </tr> </table> <p>Drying Time</p> <table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th rowspan="2">Substrate Temperature</th> <th rowspan="2">Touch dry</th> <th rowspan="2">Hard dry</th> <th colspan="2">To TOP Coat</th> </tr> <tr> <th>Minimum</th> <th>Maximum</th> </tr> </thead> <tbody> <tr> <td>25 ^oC</td> <td>2 hours</td> <td>14 hours</td> <td>7 hours</td> <td>1 month</td> </tr> <tr> <td>32 ^oC</td> <td>1 hour</td> <td>8 hours</td> <td>4 hours</td> <td>1 month</td> </tr> <tr> <td>Full Cure</td> <td colspan="4">7 days</td> </tr> </tbody> </table>	Colour	Available On Request	Gloss Level	Flat	Volume Solid	58%	Dry Film Thickness	100 – 150 microns	Number of Coat	1 or 2	Theoretical Coverage	4.60 sq.m/ℓ for 125 microns	Mixing Ratio	Base : Hardener = 4 : 1	Thinner	FOXANER 009	Pack Size	20 litres	Shelf Life	12 months	Pot Life	1.5 hours at 32 ^o C	Temperature Resistance	93 ^o C (dry)	Flash Point	Base : 25 ^o C Hardener : 45 ^o C	Substrate Temperature	Touch dry	Hard dry	To TOP Coat		Minimum	Maximum	25 ^o C	2 hours	14 hours	7 hours	1 month	32 ^o C	1 hour	8 hours	4 hours	1 month	Full Cure	7 days			
Colour	Available On Request																																																
Gloss Level	Flat																																																
Volume Solid	58%																																																
Dry Film Thickness	100 – 150 microns																																																
Number of Coat	1 or 2																																																
Theoretical Coverage	4.60 sq.m/ℓ for 125 microns																																																
Mixing Ratio	Base : Hardener = 4 : 1																																																
Thinner	FOXANER 009																																																
Pack Size	20 litres																																																
Shelf Life	12 months																																																
Pot Life	1.5 hours at 32 ^o C																																																
Temperature Resistance	93 ^o C (dry)																																																
Flash Point	Base : 25 ^o C Hardener : 45 ^o C																																																
Substrate Temperature	Touch dry	Hard dry	To TOP Coat																																														
			Minimum	Maximum																																													
25 ^o C	2 hours	14 hours	7 hours	1 month																																													
32 ^o C	1 hour	8 hours	4 hours	1 month																																													
Full Cure	7 days																																																
SURFACE PREPARATION	<p>All surfaces to be coated should be clean, dry and free from contamination.</p> <p>Concrete Allow 28 days for concrete to cure. Remove surface laitance by acid etching, abrasive or scrapping, apply direct.</p>																																																
APPLICATION DATA	<table border="0" style="width: 100%;"> <tr> <td style="padding-right: 20px;">Application Methods</td> <td></td> </tr> <tr> <td>Brush, Roller or Airless Spray</td> <td style="text-align: right;">Recommended</td> </tr> </table>	Application Methods		Brush, Roller or Airless Spray	Recommended																																												
Application Methods																																																	
Brush, Roller or Airless Spray	Recommended																																																
SAFETY PRECAUTION	<p><i>Keep away from heat, spark and Open flames. Avoid breathing of vapour on skin and eye contact. Keep container closed and store in cool, ventilated area when not in use. Proper ventilation and protective measures must be provided during mixing, application and drying, to keep vapour concentration within safe limits and to protect against topic hazard.</i></p> <p><i>Necessary safety equipment must be used and ventilation requirements carefully observed, especially in confined or enclosed spaces, such as tank interior and building.</i></p>																																																
DISCLAIMER	<p><i>The information in this product data sheet is given to the best of our knowledge based on laboratory testing and practical experience. If the product is used under condition beyond our control, we cannot guarantee anything but the quality of the products it self. The information in this product data sheet is liable for modification from time to time in the light of experience and our policy of continuous product development, and without further notice.</i></p>																																																